

测试报告

No. CKGAUTO1600994501

日期: 2016年12月20日 第1页,共4页

杭州汉高新材料科技有限公司
杭州市青山湖科技城大园路958号A幢501

以下测试之样品是由申请者所提供及确认: 热熔胶 H-700N

SGS工作编号: CQAT1612014694OH - CQ
内部编号: SHAT1612032492OH
车型: 长安 B311
制造商: 杭州汉高新材料科技有限公司
测试样品信息: 生产日期:2016.12-2 包装时间:2016.12-2
样品接收日期: 2016年12月14日
测试周期: 2016年12月14日 - 2016年12月20日
测试要求: 根据客户要求测试
测试方法: 请参见下一页
测试结果: 请参见下一页

通标标准技术服务有限公司重庆分公司
授权签名

吕廷婷

Tess Lv吕廷婷
批准签署人

备注: 根据客户申请, SGS出具了此中文报告, 英文版本可根据客户要求提供. (The Chinese test report is issued according to the applicant's request. The English version is available from SGS if further needed).



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

No. 37, Cuitao Road, Yubei District, Chongqing, China 401120 t (86-23) 63110882 f (86-23) 67613247 www.sgsgroup.com.cn
中国·重庆·渝北区翠桃路37号 邮编: 401120 t (86-23) 63110882 f (86-23) 67613247 e sgs.china@sgs.com

测试报告

No. CKGAUTO1600994501

日期: 2016年12月20日 第2页,共4页

测试结果:

测试样品描述:

样品编号	SGS样品ID	描述
SN1	CKG16-009945.001	铝箔上的透明物料

备注:

- (1) 1 mg/kg = 0.0001%
- (2) MDL = 方法检测限
- (3) ND = 未检出 (< MDL)
- (4) "-" = 未规定

气味测试

测试方法: 依据VS-01.00-T-14004-A3-2016车内非金属材料气味试验规范方法进行测试。

样品 001:

试样类型:

C

评价人员	试验条件1 强度	试验条件1 舒适度	气味描述
人员1	1.5 级	0级	-
人员2	1.5 级	0级	-
人员3	2.0 级	0级	-
试验条件类型1最终结果	1.5 级	0 级	
评价人员	试验条件3 强度	试验条件3 舒适度	气味描述
人员1	2.0 级	-1级	-
人员2	2.0 级	-1级	-
人员3	2.0 级	-1级	-
试验条件类型3最终结果	2.0 级	-1 级	



测试报告

No. CKGAUTO1600994501

日期: 2016年12月20日 第3页,共4页

备注:

1) 评分级别:

强度		舒适度	
评分级别	描述	评分级别	描述
1级	不易感觉到	3级	非常舒适
2级	可感觉到(轻微),但不刺鼻	2级	舒适
3级	可感觉到(强烈),但不刺鼻	1级	有点舒适
4级	刺鼻	0级	可接受
5级	非常刺鼻	-1级	有点不舒适
6级	不可忍受	-2级	不舒适
/		-3级	非常不舒适

2) 试样应用范围:

类型	应用范围
A	小零件,如弹簧夹头、栓塞和接管等
B	中等大小的零件,如扶手、烟灰缸、防尘罩和遮阳板等
C	大面积使用的材料,如绝缘材料、薄膜、皮革、泡沫材料、地毯、油漆和胶水等。
D	工艺胶类

3) 试验条件:

条件	温度	存放时间	湿度
1	40 ± 2℃	24 ± 1 小时	50ml去离子水/瓶
2	65 ± 2℃	2 小时 ± 10 分钟	干燥,无水
3	80 ± 2℃	2 小时 ± 10 分钟	干燥,无水

注:材料根据VS-01.00-T-14004-A3-2016车为非金属材料气味试验规范中的试验温度要求选择相应的试验温度。



SGS-CSTC 重庆分公司
Chongqing Branch Chemical Laboratory

Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

No. 37, Cuitao Road, Yubei District, Chongqing, China 401120 t (86-23) 63110882 f (86-23) 67613247 www.sgsgroup.com.cn
中国·重庆·渝北区翠桃路37号 邮编: 401120 t (86-23) 63110882 f (86-23) 67613247 e sgs.china@sgs.com



测试报告

No. CKGAUTO1600994501

日期: 2016年12月20日

第4页,共4页

样品照片:



此照片仅限于随SGS正本报告使用

*** 报告完 ***